






Characteristic	Standard	Unit	Requirement**	Result*
Modulus at 10% Elongation	ASTM D412	psi	≥300	≥300
Static Coefficient of Friction (neolite heel)	ASTM D2047	-	≥0.50 (dry)	≥0.80 (dry)
Durometer Hardness	ASTM D2240	Shore A	≥85	90
Abrasion Resistance (H18 wheel, 1000 g, 1000 cycles)	ASTM D3389	g loss	≤1.0	0.05
Critical Radiant Flux	ASTM E648	W/cm <sup>2</sup>	≥0.45	≥0.45 (Class 1)
Optical Density of Smoke	ASTM E662	-	≤450	≤450
Chemical Resistance	ASTM F925	-	≤Slight Change	Compliant***
Static Loading	ASTM F970	in	≤0.005 (at 250 psi)	0.000 (at 250 psi) 0.002 (at 800 psi)
Resistance to Heat	ASTM F1514	ΔE	≤8.0	Compliant
Resistance to Light	ASTM F1515	ΔE	≤8.0	Compliant
Tile Size	ASTM F2055	mm	±0.45	Compliant
Tile Squareness	ASTM F2055	mm	≤0.254	Compliant
Dimensional Stability of Tile	ASTM F2199	%	≤0.15	Compliant
Impact Sound Insulation	ISO 10140-3	dB	-	≈6 (ΔL <sub>w</sub> )

**Health and Environmental Attributes**

Indoor Air Quality (VOC Emissions)	AgBB	
	CA Section 01350	
	French Decree № 2011-321 (Class A+)	
	GREENGUARD Certification	
	GREENGUARD Gold	
Health-Conscious Production	Dharma is free from red listed ingredients (LBC Red List v4.0) and is manufactured <u>without</u> bisphenol A (BPA), formaldehyde, halogens, heavy metals, isocyanates, phthalates and polyvinyl chloride (PVC). HPD (Health Product Declaration) available.	
Manufacturing Plant	ISO 9001 and ISO 14001 certified plant. Floor covering manufactured using 100% renewable electric energy sources: water, wind & solar.	

Weight and Dimensions	Metric	Imperial
Thickness (ASTM F386)	2 mm (±0.15 mm)	0.079" (±0.006")
Weight	~3.1 kg/m <sup>2</sup>	~0.63 lb/ft <sup>2</sup>
Rubber Sheet Width	1.90 m	6'2"
Rubber Sheet Length	14 m [min. 6 m; max. 18 m]	45'11" [min. 19'8"; max. 59']
Rubber Tile Size	61 cm x 61 cm	24" x 24"

\*Result from manufacturing controls or third-party testing can vary between production lots, laboratories, methods and/or equipment, and as such do not constitute representations or warranties as to any particular production lot. Mondo reserves the right to modify product design and/or specifications at any time without notice.

\*\*Manufactured product must respect the minimal requirement for the characteristic listed.

\*\*\*For the complete list of chemicals tested, concentrations and contact time, please communicate with Mondo's Technical Department.